

YEAR 2018 CCIL CORRELATION

MIX DESIGN (Alberta and Yukon)

PLEASE NOTE: Mix Design Laboratories Type A are required to carry out testing only on lab mix samples as outlined below. Type A laboratories are **NOT** required to carry out additional testing on Mix Compliance (MC) samples.

Lab Mix Samples

One bag of coarse and one bag of fine aggregate for each of two mix designs (four bags total) along with asphalt cement have been provided.

Note 1. To ensure that all laboratories receive identical samples, the fine aggregate samples have been recombined from individual sieve sizes. Before commencing any testing, these samples should be **carefully but thoroughly mixed** (each fine aggregate separately) by running through a mini-splitter several times.

Note 2. Pay attention to the notes included with each weigh card

PREPARATION OF THE MATERIALS BY THE PARTICIPATING LABORATORIES

On receipt of the bulk samples of coarse and fine aggregate, dry the samples to constant mass and size the **coarse** aggregate (down to 2.5 mm size).

TESTING

AGGREGATES

Coarse aggregates shall be tested according to ASTM C127 "Density, Relative Density (Specific Gravity) and Absorption of Coarse Aggregate" and fine aggregates shall be tested according to ASTM C128, "Density, Relative Density (Specific Gravity) and Absorption of Fine Aggregate". Two determinations for each aggregate (**I-MDCA-(N)**; **II-MDCA-(N)**, **I-MDFA-(N)**; **II-MDFA-(N)**) are required. Report the "Oven Dry" Relative Density (OD) to the nearest 0.001. Calculate the absorption and report to the nearest 0.01%.

For the fine aggregate, remove the material finer than 75µm following the procedure in ASTM C117 prior to testing.

MIXES

Combine the dried aggregate and asphalt cement (**I-MDAC-(N)** or **II-MDAC-(N)**) in the proportions given on the attached mix "WEIGH CARDS", for Material A and Material B on page 3. ASTM laboratory test method D6926 "Preparation of Bituminous Specimens Using Marshall Apparatus" shall then be followed to prepare the Marshall specimens.

Note 3. Each sample for each Marshall briquette specimen and Maximum Relative Density Test is to be batched individually. A total of six (6) briquettes and two (2) Maximum Relative Density samples shall be prepared for each mix. Manual compaction of briquettes shall be carried out using **75 blows per side**. For mechanical hammers, each lab shall determine and use its own equivalency to this compaction effort.

Note 4. With the manual hammer, the following should be noted: (a) compaction pedestal must be secured; (b) the timing of blows should be 60± 5 blows per minute; (c) the hammer should be allowed to rebound between successive blows.

YEAR 2018 CCIL CORRELATION

The **mixing temperature** and **compaction temperature** shall be as indicated on the mix design weigh card forms. **Trough, moulds and hammers** shall be preheated to **135±5°C**.

Thereafter the specimens shall be tested for:

1. Bulk relative density, D2726, "Bulk Specific Gravity and Density of Non-Absorptive Compacted Bituminous Mixtures"
2. Marshall Stability and Flow, D6927, "Marshall Stability and Flow of Bituminous Mixtures".

Note 5: Stability must be reported in Newtons and Flow in 0.25mm units.

3. Maximum Specific Gravity, D2041, "Theoretical Maximum Specific Gravity and Density of Bituminous Paving Mixtures"

Note 6. To allow a proper comparison, the Maximum Specific Gravity test shall be carried out on uncompacted freshly mixed material including the heat treatment.

4. Air voids, D3203, "Percent Air Voids in Compacted Dense and Open Bituminous Pavement Mixtures"
5. VMA, TLT-301, "Determination of VMA in Compacted Bituminous Mixtures"

The Mix Design Report form shall be completed online and submitted by **January 5 2018**. An example of a completed report form is shown on page 1-4.

Hard copies of the report forms and work sheets must be submitted by **January 5 2018** by mail or courier to:

Nabil Kamel, M.A.Sc., P.Eng.
CCIL Program Manager
3410 South Service Road, Suite 104
Burlington, Ontario, L7N 3T2
Tel: 289-337-8888: Fax: 289-337-8889: [e-mail: nkamel@ccil.com](mailto:nkamel@ccil.com)

DO NOT send reports and worksheets by fax

YEAR 2018 CCIL CORRELATION

Mix Design – Material I
Weigh Card (mass in grams)

Mass Type	Coarse Aggregate I-MDCA-(N)						Fine Aggregate I-MDFA-(N)	Dust	Asphalt Cement I-MDAC-(N)
		12.5mm *	10.0mm	5.0mm	2.5mm	Pass ** 2.5mm			
Individual		18.0	196.9	280.9	12.1	5.1	627.1	39.9	66.0
Cumulative		18.0	214.9	495.8	507.9	513.0	1140.1	1180.0	1246.0

Mixing Temperature = 148°C Compaction Temperature = 135°C
AC Content (by total mass) = 5.3%

Notes:

- 1 * Is material retained on the 12.5mm sieve to be discarded? **No**
- 2 ** Is material passing the 2.5mm sieve material from coarse aggregate to be discarded? **No**
OR
Has the pass 2.5mm sieve material been included in the component package? **No**
3. *** Has dust been supplied separately? **Yes. In a separate bag with the coarse aggregate.**
4. Masses provided for BRD are to be adjusted proportionally to provide for
Maximum Theoretical Relative Density (MRD) test samples.

Mix Design – Material II
Weigh Card (mass in grams)

Mass Type	Coarse Aggregate II-MDCA-(N)						Fine Aggregate II-MDFA-(N)	Dust	Asphalt Cement II-MDAC-(N)
		12.5mm *	10.0mm	5.0mm	2.5mm	Pass ** 2.5mm			
Individual		18.5	202.7	289.1	12.4	5.3	637.6	8.2	70.9
Cumulative		18.5	221.2	510.3	522.7	528.0	1165.6	1173.8	1244.7

Mixing Temperature = 148°C Compaction Temperature = 135°C
AC Content (by total mass) = 5.7%

Notes:

1. * Is material retained on the 12.5mm sieve to be discarded? **No**
2. ** Is material passing the 2.5mm sieve material from coarse aggregate to be discarded? **No**
OR
Has the pass 2.5mm sieve material been included in the component package? **No**
3. *** Has dust been supplied separately? **Yes. In separate bags within the coarse aggregate**
4. Masses provided for BRD Specimens are to be adjusted proportionally to provide for
Maximum Theoretical Relative Density (MRD) test samples.

2018 CCIL CORRELATION – EXAMPLE REPORT AB YT

Testing Admin Information

your assigned CCIL Lab No.: **AB99**

<ul style="list-style-type: none"> • Lab Name (include Branch or Mobile #) • E-mail Address • Reported by (Contact Name) • Phone Number (Contact) • Tested by (Name(s)) • Results Reporting Date 	Apex Construction
	enstein@apex.xom
	Frank Enstein
	(999) 999-9999
	Joe Blow
	January 5 2018

* For Type A Laboratories.

MIX DESIGN - MARSHALL

Results for:	I-MD			II-MC		
Sample number	x	y	Average	x	y	Average
• BRD	2.376	2.380	2.378	2.421	2.430	2.426
• MRD	2.485	2.484	2.485	2.501	2.504	2.503
• % Voids	4.5	4.4	4.5	3.2	3.0	3.1
• % VMA	15.6	15.8	15.7	14.2	14.4	14.3
• Stability (N)	10864	11625	11245	9424	9821	9623
• Flow (0.25mm units)	10.4	10.2	10.3	9.6	10.2	9.9

Aggregate Properties

• BRD - CA	2.705	2.702	2.704	2.694	2.689	2.692
• BRD - FA	2.671	2.675	2.673	2.671	2.666	2.669
•						
• Absorption - CA	1.358	1.385	1.372	1.403	1.391	1.397
• Absorption - FA	1.741	1.728	1.735	1.766	1.744	1.755

Note: BRD values under “x” and “y” are the average of the group of 3 specimens.