

2025 CCIL Asphalt Correlation

AB YT Superpave Gyrotory Compaction – Plant Mix (PSS) Instructions

Review your shipping address shown in the portal and update it if there are any changes through the request for services. When you receive your samples, review the shipment before signing off with the shipper.

IMPORTANT NOTE: The preparation of compacted specimens is to the Design Gyration Level only. No compaction to the maximum gyration level is required. If your report requests N_{max} just enter 0.

1. PLANT SUPERPAVE SAMPLES (PSS)

In your shipment, you should have received 2 boxes of Superpave Plant Mix for 2 different mixes, **PSS-A-N for the 19.0mm mix** and **PSS-B-N for the 12.5mm mix**.

2. MAXIMUM SPECIFIC GRAVITY (G_{mm})

Determine the G_{mm} of each mix type using D2041 (latest revision). Report the value of each of the 2 replicates (i) and (ii) to 3 decimal places.

3. GYRATORY COMPACTION

The specimen preparation parameters for this testing are as follows:

| | <u>19.0mm (PSS-A)</u> | <u>12.5mm (PSS-B)</u> |
|---|-----------------------|-----------------------|
| Mass of individual gyrotory specimen, g | 4880±40 | 5045±40 |
| Recompaction temperature, °C | 142 | 142 |
| Initial number of gyrations, N_{ini} | 9 | 9 |
| Design number of gyrations, N_{des} | 125 | 125 |

For each mix type, prepare 2 specimens to the *design number of gyrations*.

4. BULK DENSITY AND % G_{mm} (Compaction Degree)

Prepare specimens, determine the bulk density of the specimens, and complete all necessary calculations, *using the latest applicable ASTM and AASHTO procedures*, to obtain % G_{mm} at N_{ini} , and the % air voids at N_{des} .

Report the values of bulk densities to 3 decimal places.

Report the values of % G_{mm} to 1 decimal place.

The Gyrotory Plant Mix test results shall be reported online and submitted by **2025 January 10, Friday**. An example of a completed report form is shown below. **Your report form should have compaction to N_{max} removed, if it is not, please enter 0.**

Remember: Your lab's worksheets must be submitted through the portal with your correlation report. Please combine all worksheets for each portal report into a single pdf prior to uploading. You are required to keep all original worksheet hard copies in a secure dedicated location such as a sealed envelope that is available to CCIL upon request. Do not courier/mail/fax/e-mail the worksheets to CCIL.

DO NOT send reports and worksheets by fax.

2025 CCIL Asphalt Correlation

AB YT Superpave Gyrotory Compaction – Plant Mix (PSS) Instructions



Gyrotory Plant Mix Report - Certification Program

▶ **CCIL Confidential Lab #** CCIL 999

▶ **Lab Name:** Demo Lab

▶ **Tested by:**

- Lab Technician
- Supervisor / Manager
- Not listed

Please specify

Super Technician

Gyrotory Plant Mix Report

| Test | A-PS-xxx (i) | A-PS-xxx (ii) | - Avg | B-PS-xxx (i) | B-PS-xxx (ii) | - Avg |
|--------------------------------------|--------------|---------------|-------|--------------|---------------|-------|
| MSG (G _{mm}) | 2.615 | 2.625 | 2.620 | 2.600 | 2.610 | 2.605 |
| BRD @ N _{des} | 2.525 | 2.535 | 2.530 | 2.520 | 2.526 | 2.523 |
| % G _{mm} @ N _{ini} | 89.2 | 89.6 | 89.4 | 88.8 | 89.2 | 89.0 |
| % Air Voids (@ N _{des}) | 3.4 | 3.4 | 3.4 | 3.1 | 3.2 | 3.2 |

Compactor Calibration

Internal Angle (1.16 deg.)

Comments