

**2025 ALBERTA AND YUKON MINI-CORRELATIONS**

**AGGREGATES and SOILS INCLUDING SUPERPAVE AGGREGATES**

Please read the following Mini-Correlation instructions carefully BEFORE you start testing!

- Testing of mini correlation samples shall be according to the below instructions.
- Submission of results by **March 28, 2025** in the mini correlation report(s) provided in the labs portal. <https://portal.ccil.com/> After signing into the portal, all mini-correlation reporting forms appropriate to your lab certification will be accessible under the tab for **Reporting Forms**. You will be able to enter your test results into the forms and submit to CCIL through the portal.
- Please record the mini-correlation sample identification information found on the sample labels in the “Comments” section of the reporting forms and upload any photos of unclear labels in the portal mini report.

**SAMPLES FOR MINI-CORRELATION TESTING**

- Samples for the mini-correlation were shipped to the laboratory March 6, 2025. If you experience delay in receiving your samples, please advise Anett Briggs [abriggs@ccil.com](mailto:abriggs@ccil.com) of your need for an extension. **Results beyond March 31<sup>st</sup> may affect your 2025 certificate being issued.**
- The mini-correlation samples are pre-prepared to meet the requirements of the appropriate test method and are to be tested as received unless instructed otherwise.
- Generally, only one sample will be shipped for each test requiring a mini-correlation. Tests for a mini-correlation are not generally carried out in pairs.
- Unsatisfactory mini result will result in a 2<sup>nd</sup> mini that must be conducted in the presence of a CCIL inspector, typically at the laboratory’s expense.

**ALBERTA AND YUKON MINI-CORRELATION INSTRUCTIONS – AGGREGATES**

**Sample Preparation**

Dry all mini-correlation aggregate samples to a constant mass at  $110 \pm 5^\circ\text{C}$ . (Drying at max  $40^\circ\text{C}$  that was needed for some of the samples tested in 2024 does not apply to any of the mini correlation samples.)

**ASTM C136: SIEVE ANALYSIS OF AGGREGATES,**

If the problem with your original test results was with the fine aggregate sieves only, your lab will receive a mini-correlation sample of fine aggregate only. See special instructions for fine aggregate samples (Fine Only) below.

Otherwise, your lab will receive a combined coarse aggregate and fine aggregate sample.

Combined

If you receive a **combined coarse and fine aggregate sample**, test the entire mini-correlation sample as specified in C136 to determine the aggregate gradation. Report the percent passing on each sieve listed in the portal report (20, 16, 12.5, 10, 5, 2.5, 1.25, 0.630, 0.315, 0.160 and 0.080 mm). All sieves are to be reported to 1 decimal (0.1%), except the 5.00 mm and 0.080 mm sieves are to be reported to two decimal places (0.01% ).

Fine Only

If you receive **only fine aggregate** for the mini-correlation sample, test the entire mini-correlation sample following C136 on the 2.5, 1.25, 0.630, 0.315, 0.160 and 0.080 mm sieves. Wash the sample according to C117 as cl. 7.7.1. indicates.

**NOTE:** Prior to reporting, carry out the following calculation: Reduce the % passing on each sieve by multiplying your results by 0.481. Failure to do so, may result in the laboratory being required to participate in a second mini correlation, typically at the laboratory’s expense.

All sieves are to be reported to 1 decimal (0.1%), except the 0.080 mm sieve is to be reported to two decimal places (0.01%).

Example for reducing the % passing on each sieve:

Sieve (mm)	Fine Aggregate % Passing of mini sample provided	Multiplication factor (% Passing 4.75mm)	Value to be reported in the portal report - (% Passing of full sample including coarse material)
2.36	77.7	x0.491	=38.1
1.18	58.2	x0.491	=28.6

**ASTM C117: WASH PASSING THE 0.08 mm SIEVE.**

Test the entire mini correlation sample as specified in C117. Report the Percent Loss to two decimal (0.01%).

---

**ASTM D4791: PERCENT FLAT AND ELONGATED PARTICLES, Type C and Type D**

The mini-correlation sample is comprised of a single test sample each, representing all of the size fractions combined. Do not separate into sized fractions. Test the portion of the sample retained on the 5mm sieve only. Test as a single fraction and report a Percent Flat and Elongated particles on that basis. For Type C and Type D Superpave Properties ASTM D4791 use a 5:1 ratio.

Report the overall weighed average the result to the nearest 0.1%. The portal allows 2 decimals but only one is required.

---

**TYPE D TESTS**

---

**ASTM C127: RELATIVE DENSITY AND ABSORPTION OF COARSE AGGREGATE**

Carry out the test as outlined in the test procedure. The mini-correlation sample size allows for duplicate testing. Report the Average Relative Density (OD) to three decimal places (0.001). Calculate and report the Average Percent Absorption and report to 2 decimal places (0.01%).

---

**ASTM D6928: MICRO-DEVAL ABRASION OF COARSE AGGREGATE**

Prepare the test specimen according to ASTM D6928 Clause 8.2. Record the Test Sample Loss to the nearest 0.1%.

Run a control sample at the same time. Report your control sample tested (Drain Brothers or MTO RM CA2), and Loss to the nearest 0.1% in the comments section of the portal report.

---

**ASTM D7428: MICRO-DEVAL ABRASION OF FINE AGGREGATE**

Prepare the test specimen according to ASTM D7428 Section 8. Record the Test Sample Loss to the nearest 0.1%.

Run a control sample at the same time. Report your control sample tested (Sutherland Sand or MTO RM FA3), and Loss to the nearest 0.1% in the comments section of the portal report.

---

## SOILS TESTS

---

### **ASTM D4318: LIQUID LIMIT, PLASTIC LIMIT AND PLASTICITY INDEX OF SOILS**

Determine the Liquid Limit, Plastic Limit and Plasticity Index of mini-correlation soil sample provided according to ASTM D 4318. Prepare the test specimens as outlined in Section 11.2 – Dry Preparation, and determine the Liquid Limit according to the procedure described in Section 12.0, Method A – Multi-point Liquid Limit. Determine the Plastic Limit using a minimum of two trials and report the mean value. Report the Liquid Limit, Plastic Limit and Plasticity Index to the nearest one decimal, i.e., 0.1 %. The portal allows 2 decimals but only one is required.

---

### **ASTM D698: PROCTOR - MOISTURE-DENSITY RELATIONSHIP**

Follow ASTM D698 Method C to perform the test on only the materials passing 19.0 mm sieve for compaction. Use the following parameters to compute correction for oversize particles:

Bulk specific gravity of the oversize fraction = 2.600  
Water content of the oversize fraction = 0.90%

Calculate corrected optimum moisture content according to equation (4) of ASTM D 4718.

Calculate corrected maximum dry density using the following equation:

$$C_{pd} = (100 \rho_F GM) / (\rho_F PC + GM PF)$$

where:

$C_{pd}$  = corrected dry density of the total material (combined finer and oversize fractions),  
GM = bulk specific gravity,  
 $\rho_F$  = dry density of the finer fraction,  
PC = Percent of oversize coarse fraction by weight, and  
PF = Percent of oversize finer fraction by weight,

Example Calculation:

Given GM = 2.60,  $\rho_F$  = 2.250, PC = 12.2%, PF = 87.8%

$$C_{pd} = (100 \times 2.250 \times 2.60) / (2.250 \times 12.2 + 2.60 \times 87.8) = 2.288$$

Report the maximum wet density in  $t/m^3$ , corrected maximum dry density in  $t/m^3$ , and corrected optimum moisture content in percentage. DO NOT REUSE THIS MATERIAL. (Note:  $t/m^3 = g/cm^3$ ).

---